



**EPAMINE PC 1820**

**CHEMICAL - PHYSICAL PROPERTIES**

Appearance : .....	Clear
Active content : .....	100%
Color Gardner : .....	<1
Brookfield viscosity (mPa.s a 25°C): .....	5 - 50
Amine value (mg KOH/g): .....	450 - 490
Average Hydrogen Equivalent : .....	81
PHR in combination with liquid epoxy resin (EEW= 190) : .....	42
Pot life 150 g at 25°C with liquid epoxy resin (EEW =190) : .....	300

*Analytical Methods can be supplied under request.*

**SEDE OPERATIVA:**

Via Fontanelle n°18, 14017 VALFENERA (AT) ITALY  
Tel: 0039 - 0141 - 939068 Fax: 0039 - 0141 - 681021

email:

[lab@pointersrl.it](mailto:lab@pointersrl.it)